

AMENDMENTS

This listing of claims replaces all prior versions and listings of claims in the application.

IN THE CLAIMS

1-10. (Canceled)

11. (Previously presented) A process comprising applying a multi-layer coating on a substrate wherein the substrate is an automotive body or part having a color-imparting and/or special effect-imparting base coat and a coating agent applied thereon as a transparent clear coat and curing said coating; wherein the coating agent contains resin solids comprising

- (a) 10 wt-% to 80 wt-% of a non-aromatic polyester polyol,
- (b) 0 wt-% to 70 wt-% of at least one constituent selected from the group consisting of hydroxyl-functional binders that are different from polyester polyol (a), hydroxyl-functional reactive thinners and combinations thereof, and
- (c) 20 wt-% to 60 wt-% of at least one cross-linking agent for the hydroxyl-functional components (a) and (b),

wherein the polyester polyol (a) is a branched structure having a calculated molecular mass from 600 to 1400, an acid value from 0 to 30 mg KOH/g and a hydroxyl value from 250 to 600 mg KOH/g with a calculated hydroxyl functionality from 4.5 to 10, and is composed of randomly positioned components consisting

- (a1) hydroxyl components comprising 0 wt-% to 20 wt-% of at least one diol and 80 wt-% to 100 wt-% of at least one polyol having 3 to 6 hydroxyl groups,
- (a2) carboxyl components comprising 0 wt-% to 20 wt-% of at least one monocarboxylic acid and 80 wt-% to 100 wt-% of at least one dicarboxylic acid, and optionally
- (a3) at least one hydroxycarboxylic acid component,

the sum of the percentages by weight of components (a) to (c), of components (a1) and of components (a2) being 100% in each case.

12. (Previously presented) A process for forming a coating layer as one coating layer of a multi-layer coating comprising:

applying to a substrate a coating layer comprising a coating agent and curing said coating layer, wherein the substrate is an automotive body or part having a color-imparting and/or special effect-imparting base coat and the coating agent applied thereon as a transparent clear coat;

wherein the coating agent contains resin solids comprising

- (a) 10 wt-% to 80 wt-% of a non-aromatic polyester polyol,
- (b) 0 wt-% to 70 wt-% of at least one constituent selected from the group consisting of hydroxyl-functional binders that are different from polyester polyol (a), hydroxyl-functional reactive thinners and combinations thereof, and
- (c) 20 wt-% to 60 wt-% of at least one cross-linking agent for the hydroxyl-functional components (a) and (b),

wherein the polyester polyol (a) is a branched structure having a calculated molecular mass from 600 to 1400, an acid value from 0 to 30 mg KOH/g and a hydroxyl value from 250 to 600 mg KOH/g with a calculated hydroxyl functionality from 4.5 to 10, and is composed of randomly positioned components consisting

- (a1) hydroxyl components comprising 0 wt-% to 20 wt-% of at least one diol and 80 wt-% to 100 wt-% of at least one polyol having 3 to 6 hydroxyl groups,
- (a2) carboxyl components comprising 0 wt-% to 20 wt-% of at least one monocarboxylic acid and 80 wt-% to 100 wt-% of at least one dicarboxylic acid, and optionally
- (a3) at least one hydroxycarboxylic acid component,

the sum of the percentages by weight of components (a) to (c), of components (a1) and of components (a2) being 100% in each case.

13. (Canceled)

14. (Canceled)

15. (Canceled)
16. (Original) The process according to claim 12, wherein the polyester polyol (a) comprises 30 wt-% to 60 wt-% of at least one hydroxyl component (a1), 30 wt-% to 70 wt-% of at least one carboxyl component (a2) and 0 wt-% to 10 wt-% of at least one hydroxycarboxylic acid component (a3).
17. (Canceled)
18. (Original) The process according to claim 12, wherein the carboxyl component (a2) consists of at least one dicarboxylic acid.
19. (Previously presented) The process according to claim 12, wherein the polyester polyol (a) comprises dimer fatty acid as one of at least two dicarboxylic acids of the carboxyl component (a2) corresponding to a weight ratio from 5 wt-% to 45 wt-% of dimer fatty acid and 55 wt-% to 95 wt-% of at least one additional dicarboxylic acid.
20. (Original) The process according to claim 12, wherein the cross-linking agent (c) is selected from the group consisting of aminoplastic resins, free polyisocyanates, blocked polyisocyanates, transesterification cross-linking agents or combinations thereof.
21. (Previously presented) The process according to claim 12, wherein the coating agent selected from the group consisting of aqueous coating agents and coating agents based on organic solvents.